

# P401M

## PAPER CORRECTING LABEL



### Description

Permanent, matte white opaque writing paper (satined) labels.

### Physical data

#### Material thickness

|                  | Value (tolerance) | Unit   | Test method  |
|------------------|-------------------|--------|--------------|
| Facestock        | 71 (+/- 3)        | micron | DIN EN 20534 |
| Adhesive         | 18                | micron |              |
| Liner (glassine) | 91                | micron | ISO 534      |

#### Paper grammage

|  | Value (tolerance) | Unit             | Test method |
|--|-------------------|------------------|-------------|
|  | 74                | g/m <sup>2</sup> | ISO 536     |

#### Adhesive (acrylic)

|                              | Value      | Unit    | Test method      |                                      |
|------------------------------|------------|---------|------------------|--------------------------------------|
| Shear strength               | > 5 hours  |         | FTM 8 - to steel |                                      |
| Initial tack                 | > 10N      |         | FTM 9 - to glass |                                      |
| Tackiness                    | Paper tear | > 15/25 | N/mm             | Contact time 0 min. FTM 1 to glass   |
|                              | Paper tear | > 15/25 | N/mm             | Contact time 20 min. FTM 1 to glass  |
|                              | Paper tear | > 16/25 | N/mm             | Contact time 24 hours FTM 1 to glass |
| Application temperature      | min. +5    | °C      |                  |                                      |
| Temperature range (adhesive) | -20 to +80 | °C      |                  |                                      |

### Certifications

Material meets REACH and RoHS requirements. Solvent free.

### Storage

Material is stable for two years stored at max. 21°C and 50% rel. humidity.  
Damp conditions, excessive heat and/or cold conditions should be avoided.

#### Disclaimer

Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available as is and that Altec gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.