

# P03500

# **ADS SLEEVES**









# Description

The Altec ADS Sleeve (PO3500) are heat shrinkable wire markers which are made of polyolefin tubing with ideal printability properties for identification purposes. The material is halogen free, flame retardant and low smoke. The compound of the tubing is without any halogens and offers excellent low fire hazard characteristics with minimal smoke emission.

| Material            | Radiation cross linked polyolefin |  |
|---------------------|-----------------------------------|--|
| Finishing           | Matt                              |  |
| Color               | Yellow, White                     |  |
| Shrink ratio        | 3:1                               |  |
| Min. shrink temp.   | > 70 °C                           |  |
| Recommended printer | Altec TTP / ATP Series            |  |

| Operation temp.  | -40°C to +125°C   |
|------------------|---|
| Liner            | White, non-coated, medium range thermal sensitive paper cardstock<br>Thickness 185 ± µm |
| Adhesive backing | Polyethylene film coated with an acrylic-<br>based pressure sensitive adhesive          |

# Physical data

#### **Technical**

| Properties          | Test Method | Typical Value   |
|---------------------|-------------|-----------------|
| Tensile Strength    | GB/T1040    | 10.4 Mpa (min.) |
| Elongation at break | GB/T1040    | ≥ 200%          |
| Longitudinal change | UL224       | +/- 5%          |

# **Electrical**

| Properties          | Test Method | Typical Value |
|---------------------|-------------|---------------|
| Dielectric strength | GB/T1408    | 15 kV/mm²     |

## Chemical

| Properties          | Test Method     | Typical Value |
|---------------------|-----------------|---------------|
| Chemical resistance | AMS-DTL-23053/5 | Good          |
| Copper corrosion    | UL224           | No corrosion  |
| Copper stability    | UL224           | No corrosion  |

**ALTEC industrial identification nv** 



#### Thermal

| Properties                    | Test Method | Typical Value                    |
|-------------------------------|-------------|----------------------------------|
| Heat shock 4 hours at 250°C   | ASTM D 2671 | No dripping, cracking or flowing |
| Heat aging 168 hours at 158°C | ASTM D 538  | Elongation 100%                  |
| Flammability                  | UL224       | Pass → flame retardant           |

#### Storage

Recommended temperature at +10°C to +25°C. (45-55% relative humidity)

### Certifications

UL UL224 recognized (file E361238) **CSA** CSA certified (file 220127)

#### **RoHS / REACH**

Based on the information about component materials which are described in our data sheets, we evaluate that we do not intentionally use the chemical substances mentioned in the paragraph < Evaluation Chemical Substances>, in a concentration above 0,1 % in state of delivery.

# **Associated regulations**

- Reach Candidate List of Substances of Very High Concern (SVHC), authorized by the European Chemicals Agency, last inclusion on the 16th July 2019.
- REACH amendment EU 2018/1513 Annex XVII
- REACH amendment EU 2018/2005 Annex XVII
- Information according to Article 33 of REACH Regulation (EC) No. 1907/2006
- RoHS directive 2011/65/EU, incl (EU)2015/863
- BRC Global Standard for Packaging and Packaging Materials Issue 5
- 517/2014/EC; certain fluorinated greenhouse gases
- 2019/1021/EG (POP) Persistent organic pollutants
- Conflict Minerals Gold, Tin, Tantalum, Tungsten
- California proposition 65 list

#### Disclaimer:

Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available as is and that Altec gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.

ALTEC industrial identification nv